



Technical Data Sheet

Phoenidur® A1100 G10

10% Glass Reinforced Acrylonitrile-Butadiene-Styrene Terpolymer (ABS)

Date: January, 2008

General

Features	Excellent stiffness Excellent dimensional stability
Appearance	Off white opaque or pigmented Pellets
Processes	Injection molding

Typical Compound Properties^(a)

	Nominal Values		Test Methods ^(b)
Physical	English Units	Metric Units	
Melt Flow Rate	2.0 g/10 min.	2.0 dg/min.	ASTM D1238, 3,800 g. @ 230°C
Specific Gravity	1.10	1.10	ASTM D792
Linear Mold Shrinkage	0.003 in/in	0.003 mm/mm	ASTM D955
Hardness, Rockwell Scale	R105	R105	ASTM D785
Coefficient of Linear Thermal Expansion	3.20 x 10 ⁻⁵ in/in °F	5.76 x 10 ⁻⁵ cm/cm °C	ASTM D696
Water Absorption	0.25%	0.25%	ASTM D785
Reinforcement Content	10±2%	10±2%	ASTM D2584

Mechanical

Notched Izod Impact @ 73 °F (23 °C)	1.3 ft-lb/in.	69.4 J/m	ASTM D256
Tensile Strength @ Yield	8,600 psi	59.3 MPa	ASTM D638
Elongation @ Yield	3%	30%	ASTM D638
Flexural Strength	15,000 psi	103.4 MPa	ASTM D790
Flexural Modulus, tangent	710,000 psi	4,897 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	220 °F	104 °C	ASTM D648
@ 264 psi (1.82 MPa)	210 °F	98 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.