



# Technical Data Sheet

## Phoensar® B2680 G30

30% Glass Reinforced Polyethylene-Terephthalate (PET) – Nucleated

Date: January, 2008

### General

Features	Excellent impact to stiffness balance Low water absorption Nucleated for faster molding cycles
Appearance	Off white opaque or pigmented Pellets
Processes	Injection molding

### Typical Compound Properties<sup>(a)</sup>

Physical	Nominal Values		Test Methods <sup>(b)</sup>
	English Units	Metric Units	
Specific Gravity	1.56	1.56	ASTM D792
Linear Mold Shrinkage	0.0025 in/in	0.0025 mm/mm	ASTM D955
Hardness, Rockwell Scale	R121	R121	ASTM D785
Coefficient of Linear Thermal Expansion	1.30 x 10 <sup>-5</sup> in/in °F	2.34 x 10 <sup>-5</sup> cm/cm °C	ASTM D696
Water Absorption	0.05%	0.05%	ASTM D785
Reinforcement Content	30±2%	30±2%	ASTM D2584

### Mechanical

Notched Izod Impact @ 73 °F (23 °C)	1.9 ft-lb/in.	101.4 J/m	ASTM D256
Tensile Strength @ Yield	21,000 psi	144.8 MPa	ASTM D638
Elongation @ Yield	5%	5%	ASTM D638
Flexural Strength	32,000 psi	220.7 MPa	ASTM D790
Flexural Modulus, tangent	1,400,000 psi	9,655 MPa	ASTM D790
Heat Deflection Temperature @ 264 psi (1.82 MPa)	435 °F	224 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.