



# Technical Data Sheet

## Phoenisol® C1600

### Polycarbonate (PC)

Date: January, 2008

#### General

Features	Excellent impact resistance Excellent surface aesthetics and clarity Naturally flame resistant
Appearance	Water white (clear) or pigmented Pellets
Processes	Injection molding

#### Typical Compound Properties<sup>(a)</sup>

	Nominal Values		Test Methods <sup>(b)</sup>
Physical	English Units	Metric Units	
Melt Flow Rate	12.0 g/10 min.	12.0 dg/min.	ASTM D1238, 1200 g. @ 300°C
Specific Gravity	1.20	1.20	ASTM D792
Linear Mold Shrinkage	0.006 in/in	0.006 mm/mm	ASTM D955
Hardness, Rockwell Scale	M70	M70	ASTM D785
Coefficient of Linear Thermal Expansion	3.75 x 10 <sup>-5</sup> in/in °F	6.75 x 10 <sup>-5</sup> cm/cm °C	ASTM D696
Water Absorption	0.15%	0.15%	ASTM D785

#### Mechanical

Notched Izod Impact @ 73 °F (23 °C)	14.0 ft-lb/in.	747.5 J/m	ASTM D256
Tensile Strength @ Yield	9,000 psi	62.1 MPa	ASTM D638
Elongation @ Yield	100%	100%	ASTM D638
Flexural Strength	14,000 psi	96.6 MPa	ASTM D790
Flexural Modulus, tangent	330,000 psi	2,276 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	195 °F	91 °C	ASTM D648
@ 264 psi (1.82 MPa)	185 °F	85 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.