



Technical Data Sheet

Phoenamide® N1100

Polyamide (Nylon) Type 6 – Impact Modified

Date: January, 2008

General

Features	Excellent chemical resistance Excellent toughness Good low temperature impact
Appearance	Off white or pigmented Pellets
Processes	Injection molding

Typical Compound Properties^(a)

Physical	Nominal Values		Test Methods ^(b)
	English Units	Metric Units	
Relative Viscosity	50.0 cP	50.0 kPa•s	ASTM D789
Melt Point	419 °F	215 °C	ASTM D789
Specific Gravity	1.10	1.10	ASTM D792
Water Absorption	1.50%	1.50%	ASTM D570
Linear Mold Shrinkage	0.012 in/in	0.012 mm/mm	ASTM D955
Hardness, Rockwell Scale	R110	R110	ASTM D785
Coefficient of Linear Thermal Expansion	6.00 x 10 ⁻⁵ in/in °F	1.04 x 10 ⁻⁴ cm/cm °C	ASTM D696

Mechanical^(c)

Notched Izod Impact @ 73 °F (23 °C)	2.5 ft-lb/in.	133.5 J/m	ASTM D256
Tensile Strength @ Yield	8,500 psi	58.6 MPa	ASTM D638
Elongation @ Break	100%	100%	ASTM D638
Flexural Strength	12,000 psi	82.8 MPa	ASTM D790
Flexural Modulus, tangent	280,000 psi	1,931 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	295 °F	146 °C	ASTM D648
@ 264 psi (1.82 MPa)	140 °F	60 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

(c) Properties measured on "Dry As Molded" test specimens.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.