



# Technical Data Sheet

## Phoenamide® N2200

### Polyamide (Nylon) Type 6/6 – High Impact

Date: January, 2008

#### General

Features	Excellent chemical resistance Excellent toughness Excellent low temperature impact resistance
Appearance	Off white or pigmented Pellets
Processes	Injection molding

#### Typical Compound Properties<sup>(a)</sup>

Physical	Nominal Values		Test Methods <sup>(b)</sup>
	English Units	Metric Units	
Relative Viscosity	50.0 cP	50.0 kPa•s	ASTM D789
Melt Point	509 °F	265 °C	ASTM D789
Specific Gravity	1.08	1.08	ASTM D792
Water Absorption	1.00%	1.00%	ASTM D570
Linear Mold Shrinkage	0.015 in/in	0.015 mm/mm	ASTM D955
Hardness, Rockwell Scale	R110	R110	ASTM D785
Coefficient of Linear Thermal Expansion	4.20 x 10 <sup>-5</sup> in/in °F	7.56 x 10 <sup>-5</sup> cm/cm °C	ASTM D696

#### Mechanical<sup>(c)</sup>

Notched Izod Impact @ 73 °F (23 °C)	16.5 ft-lb/in.	880.9 J/m	ASTM D256
Tensile Strength @ Yield	7,200 psi	49.7 MPa	ASTM D638
Elongation @ Break	50%	50%	ASTM D638
Flexural Strength	9,000 psi	62.1 MPa	ASTM D790
Flexural Modulus, tangent	235,000 psi	1,621 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	425 °F	218 °C	ASTM D648
@ 264 psi (1.82 MPa)	160 °F	71 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

(c) Properties measured on "Dry As Molded" test specimens.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.