



Technical Data Sheet

Phoenamide® N2600 G43

43% Glass Reinforced Polyamide (Nylon) Type 6/6

Date: January, 2008

General

Features	Excellent chemical resistance Excellent stiffness and elevated temperature capability
Appearance	Off white or pigmented Pellets
Processes	Injection molding

Typical Compound Properties^(a)

Physical	Nominal Values		Test Methods ^(b)
	English Units	Metric Units	
Relative Viscosity	50.0 cP	50.0 kPa•s	ASTM D789
Melt Point	509 °F	265 °C	ASTM D789
Specific Gravity	1.51	1.51	ASTM D792
Water Absorption	1.00%	1.00%	ASTM D570
Linear Mold Shrinkage	0.002 in/in	0.002 mm/mm	ASTM D955
Hardness, Rockwell Scale	M103	M103	ASTM D785
Coefficient of Linear Thermal Expansion	1.30 x 10 ⁻⁵ in/in °F	2.34 x 10 ⁻⁵ cm/cm °C	ASTM D696
Reinforcement Content	43±3%	43±3%	ASTM D2584

Mechanical^(c)

Notched Izod Impact @ 73 °F (23 °C)	2.2 ft-lb/in.	117.5 J/m	ASTM D256
Tensile Strength @ Yield	29,500 psi	203.4 MPa	ASTM D638
Elongation @ Break	2%	2%	ASTM D638
Flexural Strength	43,000 psi	296.6 MPa	ASTM D790
Flexural Modulus, tangent	1,600,000 psi	11,034 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	500 °F	260 °C	ASTM D648
@ 264 psi (1.82 MPa)	485 °F	252 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

(c) Properties measured on "Dry As Molded" test specimens.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.