



Technical Data Sheet

Phoenamide® N2610

Polyamide (Nylon) Type 6/6 – Heat Stabilized

Date: January, 2008

General

| | |
|------------|--|
| Features | Excellent chemical resistance Excellent toughness Very good elevated temperature performance |
| Appearance | Off white or pigmented Pellets |
| Processes | Injection molding |

Typical Compound Properties^(a)

| Physical | Nominal Values | | Test Methods ^(b) |
|---|----------------------------------|----------------------------------|-----------------------------|
| | English Units | Metric Units | |
| Relative Viscosity | 50.0 cP | 50.0 kPa•s | ASTM D789 |
| Melt Point | 509 °F | 265 °C | ASTM D789 |
| Specific Gravity | 1.14 | 1.14 | ASTM D792 |
| Water Absorption | 1.20% | 1.20% | ASTM D570 |
| Linear Mold Shrinkage | 0.015 in/in | 0.015 mm/mm | ASTM D955 |
| Hardness, Rockwell Scale | R121 | R121 | ASTM D785 |
| Coefficient of Linear Thermal Expansion | 4.49 x 10 ⁻⁵ in/in °F | 8.10 x 10 ⁻⁵ cm/cm °C | ASTM D696 |

Mechanical^(c)

| | | | |
|-------------------------------------|---------------|-----------|-----------|
| Notched Izod Impact @ 73 °F (23 °C) | 1.0 ft-lb/in. | 53.4 J/m | ASTM D256 |
| Tensile Strength @ Yield | 12,000 psi | 82.8 MPa | ASTM D638 |
| Elongation @ Break | 50% | 50% | ASTM D638 |
| Flexural Strength | 18,000 psi | 124.1 MPa | ASTM D790 |
| Flexural Modulus, tangent | 415,000 psi | 2,862 MPa | ASTM D790 |
| Heat Deflection Temperature | | | |
| @ 66 psi (0.455 MPa) | 455 °F | 235 °C | ASTM D648 |
| @ 264 psi (1.82 MPa) | 195 °F | 91 °C | ASTM D648 |

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

(c) Properties measured on "Dry As Molded" test specimens.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.