



# Technical Data Sheet

## Phoeneos® P1500 GC13

### 13% Glass Coupled Polypropylene (PP) Homopolymer

Date: January, 2008

#### General

Features	Good stiffness and high temperature capability Excellent chemical resistance Good balance of properties
Appearance	Off white or pigmented Pellets
Processes	Injection molding

#### Typical Compound Properties<sup>(a)</sup>

Physical	Nominal Values		Test Methods <sup>(b)</sup>
	English Units	Metric Units	
Melt Flow Rate	12.0 g/10 min.	12.0 dg/min.	ASTM D1238, 2160 g. @ 230°C
Melt Point	334 °F	168 °C	ASTM D789
Specific Gravity	0.99	0.99	ASTM D792
Linear Mold Shrinkage	0.007 in/in	0.007 mm/mm	ASTM D955
Hardness, Rockwell Scale	R94	R94	ASTM D785
Coefficient of Linear Thermal Expansion	3.00 x 10 <sup>-5</sup> in/in °F	5.40 x 10 <sup>-5</sup> cm/cm °C	ASTM D696
Reinforcement Content	13±2%	13±2%	ASTM D2584

#### Mechanical

Notched Izod Impact @ 73 °F (23 °C)	1.1 ft-lb/in.	58.7 J/m	ASTM D256
Tensile Strength @ Yield	7,600 psi	52.4 MPa	ASTM D638
Elongation @ Break	4%	4%	ASTM D638
Flexural Strength	9,000 psi	62.1 MPa	ASTM D790
Flexural Modulus, tangent	425,000 psi	2,931 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	293 °F	145 °C	ASTM D648
@ 264 psi (1.82 MPa)	248 °F	120 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.