



Technical Data Sheet

Phoeneos® P1600 TL40

40% Talc Reinforced Polypropylene (PP) Homopolymer

Date: January, 2008

General

Features	Excellent dimensional stability Excellent chemical resistance Good balance of structural properties
Appearance	Off white or pigmented Pellets
Processes	Injection molding

Typical Compound Properties^(a)

	Nominal Values		Test Methods ^(b)
Physical	English Units	Metric Units	
Melt Flow Rate	6.0 g/10 min.	6.0 dg/min.	ASTM D1238, 2160 g. @ 230°C
Melt Point	334 °F	168 °C	ASTM D789
Specific Gravity	1.24	1.24	ASTM D792
Linear Mold Shrinkage	0.007 in/in	0.007 mm/mm	ASTM D955
Water Absorption	0.03%	0.03%	ASTM D570
Hardness, Rockwell Scale	R95	R95	ASTM D785
Coefficient of Linear Thermal Expansion	2.40 x 10 ⁻⁵ in/in °F	4.32 x 10 ⁻⁵ cm/cm °C	ASTM D696
Reinforcement Content	40±2%	40±2%	ASTM D2584

Mechanical

Notched Izod Impact @ 73 °F (23 °C)	0.7 ft-lb/in.	37.4 J/m	ASTM D256
Gardner Impact @ 73°F (23 °C)	6.0 in-lb.	0.4 joules	ASTM D638
Tensile Strength @ Yield	4,500 psi	31.0 MPa	ASTM D638
Elongation @ Break	10%	10%	ASTM D638
Stiffness In Flexure	320,000 psi	2,207 MPa	ASTM D747
Flexural Modulus, tangent	500,000 psi	3,448 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	275 °F	135 °C	ASTM D648
@ 264 psi (1.82 MPa)	175 °F	79 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.