



Technical Data Sheet

Phoenistyr® S2100 G10

10% Glass Reinforced Polystyrene – High Impact (HIPS)

Date: January, 2008

General

Features	High Stiffness Good impact resistance Easy processing
Appearance	Off white opaque or pigmented Pellets
Processes	Injection molding

Typical Compound Properties^(a)

Physical	Nominal Values		Test Methods ^(b)
	English Units	Metric Units	
Melt Flow Rate	5.0 g/10 min.	5.0 dg/min.	ASTM D1238, 5000 g. @ 200°C
Specific Gravity	1.13	1.13	ASTM D792
Linear Mold Shrinkage	0.003 in/in	0.003 mm/mm	ASTM D955
Hardness, Rockwell Scale	R110	R110	ASTM D785
Coefficient of Linear Thermal Expansion	2.20 x 10 ⁻⁵ in/in °F	3.96 x 10 ⁻⁵ cm/cm °C	ASTM D696
Vicat Softening Point	203 °F	95 °C	ASTM D1525, Rate B, 50N load

Mechanical

Notched Izod Impact @ 73 °F (23 °C)	1.5 ft-lb/in.	80.1 J/m	ASTM D256
Tensile Strength @ Yield	5,500 psi	37.9 MPa	ASTM D638
Elongation @ Break	3%	3%	ASTM D638
Flexural Modulus, tangent	450,000 psi	3,103 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	205 °F	96 °C	ASTM D648
@ 264 psi (1.82 MPa)	190 °F	87 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.