



# Technical Data Sheet

## Phoenistyr® S3600 G20

### 20% Glass Reinforced Styrene-Acrylonitrile (SAN) Copolymer

Date: January, 2008

#### General

Features	High Stiffness Excellent structural properties
Appearance	Off white opaque or pigmented Pellets
Processes	Injection molding

#### Typical Compound Properties<sup>(a)</sup>

Physical	Nominal Values		Test Methods <sup>(b)</sup>
	English Units	Metric Units	
Melt Flow Rate	4.0 g/10 min.	4.0 dg/min.	ASTM D1238, 5000 g. @ 200°C
Specific Gravity	1.22	1.22	ASTM D792
Linear Mold Shrinkage	0.002 in/in	0.002 mm/mm	ASTM D955
Hardness, Rockwell Scale	R122	R122	ASTM D785
Coefficient of Linear Thermal Expansion	1.80 x 10 <sup>-5</sup> in/in °F	3.24 x 10 <sup>-5</sup> cm/cm °C	ASTM D696
Water Absorption	0.12%	0.12%	ASTM D785
Reinforcement Content	20±2%	20±2%	ASTM D2584

#### Mechanical

Notched Izod Impact @ 73 °F (23 °C)	0.7 ft-lb/in.	37.4 J/m	ASTM D256
Tensile Strength @ Yield	15,000 psi	103.4 MPa	ASTM D638
Elongation @ Break	2%	2%	ASTM D638
Flexural Modulus, tangent	1,100,000 psi	7,586 MPa	ASTM D790
Heat Deflection Temperature			
@ 66 psi (0.455 MPa)	225 °F	107 °C	ASTM D648
@ 264 psi (1.82 MPa)	215 °F	102 °C	ASTM D648

(a) Values shown represent nominal averages and are not to be construed as product specifications.

(b) ASTM methods are the latest under the Society's current Procedures. All Molded specimens are prepared by injection molding.

Manufacturer makes no warranties as to the fitness for any purpose or the merchantability of any products referred to herein, no guarantee of satisfactory results from any use of, or reliance upon the information or data contained herein, and no guarantee that the use of any product will not infringe any patent. Manufacturer hereby disclaims all liability for any loss or damage resulting from the use of information and data contained herein.